

Status as at: 11 March 2019

## EVALUATION CRITERIA DOCUMENT

### **Annexes to evaluation criteria document for plastics and other organic materials in contact with drinking water (KTW-BWGL)**

### **Polymer-specific part**

English translation – only the German document version is legally binding

German Environment Agency  
Section II 3.4  
Heinrich-Heine-Str. 12  
08645 Bad Elster, Germany

[www.umweltbundesamt.de](http://www.umweltbundesamt.de)

# **Annex A           Plastics**

## **A.1       Scope of application**

### **A.1.1   Plastics**

Materials whose main components consist of macromolecular organic compounds that are produced synthetically or by modifying natural products are designated as plastics (as per DIN EN 472:2013-06). In many cases, under specific conditions (heat and pressure), they can be melted and moulded. Plastics are organic materials consisting mainly of polymers with a high molecular weight. These polymers are macromolecular substances manufactured from monomers and other starting substances using a polymerisation process such as polyaddition, polycondensation or similar. Organic coatings, adhesives, elastomers, lubricants and silicones do not come under this scope of application.

In addition to polymers made up of monomers as the main structural component, additives may also be contained in plastics, which give specific properties during the manufacturing process or in the end product.

Aids to polymerisation (AtP) may also be contained in the plastic. They initiate polymerisation and/or control the formation of the macromolecular structure (e.g. catalysts, accelerators) and are used in very low quantities. They may be present in the end product but are not intended to be there.

Polymer production aids (PPA) are used in the manufacture of plastics. They only have a function in the manufacturing process and are not intended to have any effects in the end-product. However, they may be present in the end-product.

In food law, the requirements for manufacturing plastic materials and articles are regulated in Regulation (EU) No 10/2011 on plastic materials and articles that are intended to come into contact with food. The starting materials listed therein may also be used for the manufacture of plastics intended to come into contact with drinking water.

### **A.1.2   Crosslinked plastics**

Crosslinked plastics have polymer chains linked with covalent bonds. Crosslinked polyethylene (PE-X) is mainly significant for products in contact with drinking water. Crosslinking can be carried out using various processes: Crosslinked polyethylene can be manufactured using peroxides (PE-X<sub>a</sub>), using silanes (PE-X<sub>b</sub>) or by high-energy radiation (PE-X<sub>c</sub>). Crosslinking agents currently used are only partly listed in Regulation (EU) No 10/2011. Therefore, additional crosslinking agents are listed in the supplementary positive list in this evaluation criteria document.

### **A.1.3   Recycled plastics**

The use of recycled plastics is restricted to the use of offcuts and scraps generated by the producer that are uncontaminated and not yet placed on the market. It must be ensured that the formulation of the recycled materials is known and can be indicated and tested.

## A.2 Positive list of starting substances for the manufacture of plastics

Only the substances approved in Regulation (EU) No 10/2011 (EU list) and those listed in Table A-1 may be used to manufacture plastics in contact with drinking water.

Aids to polymerisation, solvents and colourants are not regulated in Regulation (EU) No 10/2011 and can be regulated under national food law. Where these starting substances are not included in Table A-1, the requirements for unlisted starting substances apply, including their contaminants and degradation and reaction products (see Chapter 5.2.2 of the general part of the evaluation criteria for organic materials). The requirements according to Chapters 5.4.2 and 5.4.3 of the general part of the evaluation criteria for organic materials apply to fillers and colourants.

Table A-1: Supplementary positive list for plastics in contact with drinking water

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
<b>Monomers</b>				
-	7782-41-4	Fluorine* (decision by 4MS-Initiative pending)	150 as fluoride (F) 1.0 for perfluorobutanoic acid (PFBA) 0.3 for perfluoropentanoic acid (PFPeA) 0.6 for perfluorohexanoic acid (PFHeA)	
<b>Additives and polymer production aids</b>				
-	7637-07-2	Boron trifluoride**	100 as B 150 als fluoride	
40430	109-63-7	Boron trifluoride etherate**	100 as B 150 as fluoride	
4120	7789-75-5	Calcium fluoride**	150 as fluoride	
-	21679-31-2	Chromium (III) acetylacetonate**	5 as Cr	
-	25182-44-9	Chromium methacrylate**	5 as Cr 300 as methacrylic acid	
56320	1323-83-7	Glyceryl distearate**		
-	12136-45-7	Potassium oxide**		
-	1313-59-3	Sodium oxide**		
-	7782-99-2	Sulfurous acid*	500 as SO <sub>2</sub>	
95870	-	Wheat protein**		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
<b>Aids to polymerisation</b>				
-	10025-73-7	Chromium (III) chloride**	5 as Cr	
-	11118-57-3	Chromium oxide**	5 as Cr	
47080	110-05-4	Di- <i>tert.</i> -butyl peroxide*	0.1 15 for methyl- <i>tert.</i> -butyl ether (MtBE) 500 for <i>tert.</i> -butanol	
49160	127-19-5	N,N-Dimethyl - acetamide (DMAC)*	2.5	
59330	110-54-3 EC-Nr. 925-292-5	n-Hexane (incl. structural isomers up to 40 %)*	250	MTC <sub>tap</sub> for n-hexane need not be tested if the process temperature is over 100 °C
-	93685-81-5 (13475-82-6)	Isododecane (main isomer: 2,2',4,6,6'-pentamethyl-heptane)**	2.5	
23680 81280	9002-89-5	Polyvinyl alcohol**		manufactured by sintering
-	7782-44-7	Oxygen**		

\* Substances that are assessed nationally

\*\* Substances that are assessed by another EU Member State as part of the 4MS initiative and adopted by the other states (listed in the 4MS Core List)

### A.3 Additional requirements for plastics

The additional requirements for plastics laid down in Table A-2 apply. The general part of the evaluation criteria for organic materials must be observed.

Table A-2: Additional requirements for plastics

Substances/substance groups	MTC <sub>tap</sub> in µg/l	Test method (Other equivalent test methods may be used)
Total primary aromatic amines (PAA) <sup>1</sup> in plastics containing PAA or whose manufacture may result in the presence of PAAs (e. g. polyamide, polyurethane)	0.1	specific detection by GC-ECD/GC-MS with derivatisation <sup>2</sup>
Where substances from the following group are used:		
Metals used as catalysts	10 % of the relevant limit value of TrinkwV (e.g. nickel 2 µg/l)	DEV <sup>3</sup>
Fillers	Requirements according to 5.4.2 of the general part of the Evaluation Criteria Document	
Colourants	Requirements according to 5.4.3 of the general part of the Evaluation Criteria Document	

<sup>1</sup> Except PAAs allowed in Regulation 10/2011.

<sup>2</sup> Test method: Pietsch et al. (1996) Fresenius J. Anal. Chem. 355:164-173 or Pietsch et al. (1997) Vom Wasser 88: 119-135

<sup>3</sup> German standard methods for the examination of water, waste water and sludge (Deutsche Einheitsverfahren (DEV) zur Wasser-, Abwasser- und Schlammuntersuchung)

# Annex B            Organic coatings

## B.1    Scope of application

This annex applies to materials described below:

Coatings as envisaged in this evaluation criteria document are products made from substances – or mixtures of predominantly organic substances – which in their final state do not themselves form a load-bearing layer, but which in case of application on a substrate (metals, cementitious materials) form a solid layer with a particular technological effect.

Coatings are produced from coating substances by means of application (DIN 55945: 2016-08). Coating substances are usually processed by means of procedures such as spreading, immersing, filling, spraying etc.

Coating systems used in contact with drinking water may have a multi-layer structure (base, intermediate and finish coat). The assessment can be conducted as a complete system or each layer can be assessed separately in accordance with Chapter 5.7.

Organic coatings contain resins and curing agents as binding agents. These can be epoxy resins, polyurethane or polyester for example.

This annex also applies to the following reactive systems:

- **Resins** used for example as paint resins for coatings, as impregnating resins, injection resins or for chemically curing adhesives
- **Aqueous plastic dispersions**

## B.2    Information on organic coatings

### B.2.1    Various products

**Resins** are solid to liquid organic polymers and oligomers with an amorphous structure when dry. These include:

- **Impregnating resins** are liquid or liquefiable resins that serve for soaking and impregnating porous materials such as casting materials. The pores set when the resin hardens. Epoxy resins, unsaturated polyester resins, polyurethane resins and acrylic resins are used as a basis for impregnating resins.
- **Injection resins** are liquid or liquefiable resins used to pressure fill cracks in the basic material and that set after hardening. Epoxy resins, polyurethane resins or polyester resins are commonly used as a basis for injection resins.
- **Adhesives** (as per DIN EN 923: 2008-06) are non-metallic materials that bond two surfaces by surface adherence (adhesion) and internal strength (cohesion).

Single-component reaction adhesives:

Single-component reaction adhesives cure on the basis of external influences. These can be systems that react to moisture, that use water in substrates or ambient air, or radiation curing adhesives where polymerisation is started in UV light. Adhesives based on acrylates are examples of radiation curing adhesives. The advantage of this type of polymerisation is that the adhesive only solidifies as and when needed

because the reaction only begins when sufficient light of a specific wavelength is available. The curing times required for these adhesives are generally short, typically in the range of 0.5-60 seconds.

Multi-component reaction adhesives:

Most multi-component reaction adhesives are mixed from two components (two-component adhesives). The raw material is combined with a curing agent or activator. Reaction adhesives can cure (set) through various mechanisms. Reaction adhesives made of epoxy resins and anhydrides or polyamines (epoxy resin adhesives) react after polyaddition mechanisms, cyanoacrylate (cyanoacrylate adhesives) or methacrylate (methacrylic ester) after polymerisation mechanisms, and systems based on aminoplasts or phenoplasts (see phenolic resins) after polycondensation mechanisms.

- **Casting resins** are synthetic resins that are liquid or liquefiable after moderate warming, that are poured into open moulds and that can be cured therein without any application of pressure. Casting resins include reaction resins such as epoxy resins, formaldehyde resins, isocyanate resins, methacrylic resins and unsaturated polyester resins. **Sealing compounds** made from plastic, e.g. polyamides, are casting resins in which other components are moulded. Among other things, this protects parts against the penetration of moisture, dust, foreign particles, water, etc.

**Aqueous plastic dispersions** contain thermoplastics finely distributed in water and are stable colloidal systems. Acrylic resins are used inter alia as binding agent systems for plastic dispersions. Aqueous plastic dispersions can be used as surface protection systems or dispersion adhesives for example.<sup>4</sup>

**Anaerobic adhesives** are reactive sealants that only harden in the presence of metals and in the absence of oxygen. They are used for the adhesive bonding of threaded connections, for example angle valves or for the adhesive bonding of connections in the tap.

For anaerobic adhesives only the provisions set out in Chapter B.5 apply.

#### **Coatings with cementitious fillers (polymer content > 25 % (w/w) related to cement)**

Cementitious materials can be assessed for suitability in contact with drinking water according to DVGW standard W 347<sup>5</sup>. Conventional cementitious materials contain only small quantities of organic additives such as concrete admixtures. Where large quantities of polymers are added to the cementitious materials (> 25 % (w/w) with regard to the dry matter cement content) the migration behaviour of the materials is comparable to organic coatings. Cementitious fillers are listed in the positive list for organic coatings in Table B-1.

---

<sup>4</sup> Roland Benedix, *Bauchemie - Einführung in die Bauchemie für Ingenieure*, 3. Auflage, Teubner, 2006, S. 457 ff.

<sup>5</sup> Once the evaluation criteria document for cementitious materials is published, this must be used to assess the suitability in contact with drinking water of cementitious materials with an organic proportion < 25 % (w/w).

## B.2.2 Composition information

Coating substances and other products under this evaluation criteria document generally consist of the following main components:

- Binding agents (resins and curing agents if any),
- Fillers and colourants,
- Organic modifying agents,
- Solvents and thinners,
- Additives and polymer production aids,
- Aids to polymerisation.

The **binding agent** of a coating substance is considered to be the non-volatile component of the binding agent solution or dispersion, which forms the coating (DIN EN 941-1:1996).

Binding agents are polymer components of coatings and determine the type of coating (see B.2.3, Information on crosslinking conditions). The starting substances for binding agents are to be understood as monomers as defined in Regulation (EU) No 10/2011.

**Fillers and colourants** provide mechanical stabilisation and coloration. Fillers enhance the protective function. They enhance the applicability of the coating substance by giving it a viscous consistency.

**Organic modifying agents** serve among other things to enhance usability and/or drying properties.

**Solvents** are used to lower viscosity in order to enhance applicability. They should not remain present after the curing process. In aqueous or water-dilutable coatings, water is used as a solvent or thinner.

**Additives and polymerisation production aids** are used to increase:

- the shelf life of starting substances and preparations,
- performance characteristics (e.g. rheological additives to enhance flow properties such as runoff behaviour and smoothness),
- film quality (e.g. anti-foam additives to prevent formation of bubbles, pores and craters,
- wetting of the substrate surface,
- the surface structure.

Due to the multiple functions of the listed starting substances, no distinction is made between additives and polymerisation production aids (PPA)

**Aids to polymerisation** may also be contained in the plastic.

### **Binding agent systems:**

Resins based on Bisphenol A diglycidyl ether; Bisphenol F diglycidyl ether and other glycidyl ethers with various molecular weights are used in the case of **epoxy resins**. Curing agents may be amines, amido-amines and amine adducts, whose amine hydrogens react with the



epoxy groups. Isocyanates can be other curing agents. Other compounds, such as acids or other H-active compounds, can also be used as curing agents.

In **polyurethane coatings**, isocyanates and compounds containing hydroxyl groups (polyols) may be used as binding agents. The combination of isocyanates with amino-functional compounds produces polycarbamide coatings.

**Polyesters** contain polyester compounds as their binding agents, which are produced through esterification of polyvalent alcohols and polycarbonic acids, and may be crosslinked with isocyanates for example.

**Acrylic resins** are crosslinked synthetic resins obtained by the polymerisation of acrylic acid esters and methacrylic acid esters. They comprise functional groups (hydroxyl-, N-hydroxymethyl, carboxyl and epoxy groups), used for crosslinking. Acrylic resins can be crosslinked internally or externally (e.g. after adding polyisocyanates, epoxy resins or polycarbonic acids).

Coating systems used in contact with drinking water may have a multi-layer structure (base, intermediate and finish coat). The assessment can be conducted as a complete system or each layer can be assessed separately in accordance with Chapter 5.7.

### **B.2.3 Information on crosslinking conditions**

Cold curing binding agents must cure at ambient temperature and are generally not heated after application (where necessary, they can be force dried with moderately heated air). Hot-curing binding agents are heated or annealed until cured. The curing time for cold curing systems depends on their composition and on ambient temperature during curing. In some cases, it can take more than 2 weeks before it is usable. Hot-curing systems are ready for use after the annealing time, typically less than an hour.

A further distinction is made between solvent-based and solvent-free binding agent systems. Solvent-free binding agents may be used to produce thicknesses of up to 2 000 µm in a single application. Solvent-based binding agents may only be only applied in thin layers, since the solvent contained in them needs to evaporate to the surface before this is prevented by the physical drying process and/or the ongoing reaction of the reactive components.

## **B.3 Composition requirements**

### **B.3.1 Positive list of starting substances for the manufacture of organic coatings**

Only the starting substances listed in Table B-1 may be used to manufacture organic coatings in contact with drinking water.

For unlisted starting substances, the requirements for unlisted starting substances apply, including their contaminants and degradation and reaction products (see Chapter 5.2.2 of the general part of the evaluation criteria document for organic materials). The requirements

according to Chapters 5.4.2 and 5.4.3 of the general part of the evaluation criteria document for organic materials apply to fillers and colourants.

Table B-1 Starting substances for coatings assessed by the UBA or recognised as part of the 4MS cooperation

### B.3.1.1 Starting substances for resins and curing agents

#### B.3.1.1.1 Phenolic compounds

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13480 13607	80-05-7	2,2-Bis(4-hydroxyphenyl)-propane (Bisphenol A)	2.5 <sup>6</sup>	
14020	98-54-4	p-tert-Butylphenol	2.5	
14710	108-39-4	m-Cresol		
14740	95-48-7	o-Cresol		
14770	106-44-5	p-Cresol		
15880 24051	120-80-9	1,2-Dihydroxybenzene	300	
15910 24072	108-46-3	1,3-Dihydroxybenzene	120	
15940 18867	123-31-9	1,4-Dihydroxybenzene	30	
16000	92-88-6	4,4'-Dihydroxybiphenyl	300	
16360	576-26-1	2,6-Dimethylphenol	2.5	
22960	108-95-2	Phenol		
25927	27955-94-8	1,1,1-Tris(4-hydroxyphenyl)-ethane	0.25	
-	8007-24-7	Cashew nut shell oil, distilled (>90% Cardanol)*	2.5	not as reaktive diluent

#### B.3.1.1.2 Aldehydes

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
10060	75-07-0	Acetaldehyde	300	
14110	123-72-8	Butyraldehyde		
17260	50-00-0	Formaldehyde	750	
23860	123-38-6	Propionaldehyde		

<sup>6</sup> <https://www.umweltbundesamt.de/en/document/new-regulation-on-bisphenol-a-consequences-for>

### B.3.1.1.3 Oxirane and glycidyl compounds

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13160 22552	28064-14-4	Novolac glycidyl ether (NOGE)*	2.5	for powder paints only
13460 12976	54208-63-8 57469-07-5 39817-09-9 2095-03-6 9003-36-5	Bisphenol-F-diglycidyl ether*	2.5	
13510 13610	1675-54-3	Bisphenol-A-diglycidyl ether*	450	
13780	2425-79-8	1,4-Butanediol diglycidyl ether	0.1	QM = 1 mg/kg
16750 14570	106-89-8	Epichlorohydrin	0.1	
17020	75-21-8	Ethylene oxide	0.1	QM = 1 mg/kg
21823	598-09-4	2-Methyl epichlorohydrin*	0.1	
24010	75-56-9	Propylene oxide	0.1	QM = 1 mg/kg
25360		Trialkyl(C5-C15)acetic acid, 2,3-epoxypropyl ester	0.1	QM = 1 mg/kg
88640	8013-07-8	epoxidised soybean oil	TOC	

### B.3.1.1.4 Amines

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
12670	2855-13-2	1-Amino-3-aminomethyl-3,5,5-trimethyl cyclohexane	300	
12761	693-57-2	12-Aminododecanoic acid	2.5	
12763 35170	141-43-5	2-Aminoethanol	2.5	
12788	2432-99-7	11-Aminoundecanoic acid	250	
12789 35320	7664-41-7	Ammonia	50 as NH <sub>4</sub> <sup>+</sup>	
13000	1477-55-0	1,3-Benzene-dimethanamine	2.5	
13075 15310	91-76-9	2,4-Diamino-6-phenyl-1,3,5-triazine	250	
13210	1761-71-3	Bis(4-aminocyclohexyl) methane	2.5	

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13250	101-77-9	Bis(4-aminophenyl) methane**	0.1	
15250	110-60-1	1,4-Diaminobutane		
15695	461-58-5	Dicyanodiamide		
15790	111-40-0	Diethylenetriamine	250	
16145	124-40-3	Dimethylamine*	3	
16150	108-01-0	Dimethylamino ethanol	900	
16960 15272	107-15-3	Ethylenediamine	600	
17005	151-56-4	Ethyleneimine	0.1	
18460 15274	124-09-4	Hexamethylenediamine	120	
18670	100-97-0	Hexamethylenetetramine	750 as form- aldehyde	
21754	15520-10-2	2-Methyl-1,5- diaminopentane*	5	
21765	106246-33-7	4,4'-Methylene-bis(3-chloro- 2,6-diethylaniline)	2.5	
22331	25513-64-8	mixture of (35-40 %) 1,6- Diamino-2,2,4- trimethylhexane and (55- 65 %) 1,6-Diamino-2,4,4- trimethylhexane	2.5	
23050	108-45-2	1,3-Phenylenediamine	0.1	
25180	102-60-3	N,N,N',N'-Tetrakis(2- hydroxy-propyl)ethylene diamine		
25420 19975	108-78-1	2,4,6-Triamino-1,3,5-triazine	1500	
25960	57-13-6	Urea		
45760	108-91-8	Cyclohexylamine		
94560	122-20-3	Triisopropanolamine	250	
-	936-49-2	2-Phenylimidazoline*	2.5	
	9046-10-0	Polyoxypropylene diamine*	2.5	Specification of minimum content of 80 % polyoxy- propylene- diamine and an average molecular weight ≥ 230 Da

### B.3.1.1.5 Isocyanates

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
14877	2556-36-7	1,4-Cyclohexylene diisocyanate**	0.1	QM(T) = 1 mg/kg as NCO
14950	3173-53-3	Cyclohexyl isocyanate	0.1	
15700	5124-30-1	Dicyclohexylmethane-4,4'-diisocyanate	0.1	
16240	91-97-4	3,3'-Dimethyl-4,4'-diisocyanatobiphenyl	0.1	
16570	4128-73-8	Diphenylether-4,4'-diisocyanate	0.1	
16600	5873-54-1	Diphenylmethane-2,4'-diisocyanate	0.1	
16630	101-68-8	Diphenylmethane-4,4'-diisocyanate	0.1	
16920	87057-87-2	2-Ethylbutane-1,4-diisocyanate**	0.1	
18640	822-06-0	Hexamethylene diisocyanate	0.1	
19110 19147	4098-71-9	1-Isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane	0.1	
22065	34813-62-2	2-Methylpentane-1,5-diisocyanate**	0.1	
22420	3173-72-6	1,5-Naphthalene diisocyanate	0.1	
22570	112-96-9	Octadecyl isocyanate	0.1	
23060	104-49-4	1,4-Phenylene diisocyanate**	0.1	
23125	103-71-9	Phenyl isocyanate**	0.1	
25208	26471-62-5	Toluene diisocyanate	0.1	
25210	584-84-9	2,4-Toluene diisocyanate	0.1	
25240	91-08-7	2,6-Toluene diisocyanate	0.1	
25270	26747-90-0	2,4-Toluene diisocyanate dimer	0.1	
25445	28807-72-9	Tricyclodecane diisocyanate**	0.1	
25573	16938-22-0	2,2,4-Trimethylhexane-1,6-diisocyanate**	0.1	
25574	15646-96-5	2,4,4-Trimethylhexane-1,6-diisocyanate**	0.1	

### B.3.1.1.6 Diols/Polyols

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13390 14880	105-08-8	1,4-Bis(hydroxymethyl)-cyclohexane		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13690	107-88-0	1,3-Butanediol		
13720 40580	110-63-4	1,4-Butanediol	250	
14500 43280	9004-34-6	Cellulose		
15760 13326 47680	111-46-6	Diethylene glycol	TOC	
16390 22437	126-30-7	2,2-Dimethyl-1,3-propanediol, Neopentyl glycol	2.5	
16480	126-58-9	Dipentaerythritol		
16660 13550	110-98-5 25265-71-8	Dipropylene glycol		
16925 53280	9004-57-3	Ethylcellulose		
16990 53650	107-21-1	Ethylene glycol (1,2-Ethanediol)	TOC	
17530	50-99-7	Glucose		
18100	56-81-5	Glycerol		
18700	629-11-8	1,6-Hexanediol	2.5	
19972 65520	87-78-5	Mannitol		
22190	2163-42-0	2-Methyl-1,3-propanediol**	250	
22840	115-77-5	Pentaerythritol		
23590	25322-68-3	Polyethylene glycol		
23651	25322-69-4	Polypropylene glycol		
23740 81840	57-55-6	1,2-Propanediol		
23770	504-63-2	1,3-Propanediol	2.5	
24490	50-70-4	Sorbitol		
24880	57-50-1	Sucrose		
25090	112-60-7	Tetraethylene glycol		
25510	112-27-6	Triethylene glycol		
25600 13380	77-99-6	1,1,1-Trimethylolpropane	300	
25910	24800-44-0	Tripropylene glycol		

### B.3.1.1.7 Monoalcohols

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
12375 33120	-	Alcohols, aliphatic, monohydric, saturated, linear, primary (C <sub>4</sub> -C <sub>22</sub> )		
13150	100-51-6	Benzyl alcohol		
13840	71-36-3	1-Butanol		
13845	75-65-0	tert-Butanol*	500	
15100	112-30-1	1-Decanol		
16701	112-53-8	1-Dodecanol**		
16780	64-17-5	Ethanol		
17050	104-76-7	2-Ethyl-1-hexanol	TOC	
17160	97-53-0	Eugenol	0.1	
18150	111-70-6	1-Heptanol**		
18310	36653-82-4	1-Hexadecanol		
18780	111-27-3	1-Hexanol**		
21550	67-56-1	Methanol		
22480	143-08-8	1-Nonanol		
22555	112-92-5	1-Octadecanol**		
22600	111-87-5	1-Octanol		
22766 69760	143-28-2	Oleyl alcohol		
22870	71-41-0	1-Pentanol		
23800	71-23-8	1-Propanol		
23830	67-63-0	2-Propanol		
25070	112-72-1	1-Tetradecanol**		

### B.3.1.1.8 Oils and acids

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
10030	514-10-3	Abietic acid		
10090 30000	64-19-7	Acetic acid		
10150	108-24-7	Acetic anhydride		
10599/90A 10599/91	61788- 89-4	Dimers of unsaturated fatty acids (C <sub>18</sub> ), non-hydrogenated, distilled and non-distilled	2.5	
10599/92A 10599/93	68783- 41-5	Dimers of unsaturated fatty acids (C <sub>18</sub> ), hydrogenated, distilled and non-distilled		
10690	79-10-7	Acrylic acid	300	

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
12130	124-04-9	Adipic acid		
12280	2035-75-8	Adipic anhydride		
12810	506-30-9	Arachidic acid**		
12813	7771-44-0	Arachidonic acid**		
12820	123-99-9	Azelaic acid		
12970	4196-95-6	Azelaic anhydride		
12980	8015-74-5	Beechnut oil**		
12990	112-85-6	Behenic acid**		
13090	65-85-0	Benzoic acid		
13620	10043-35-3	Boric acid	100 for B	
14140	107-92-6	Butyric acid		
14320	124-07-2	Caprylic acid		
14411 42880	8001-79-4	Castor oil		
14440 42960	64147-40-6	Castor oil, dehydrogenated		
14445	61789-44-4	Castor oil fatty acids**		
14450/1	-	Castor oil fatty acids, dehydrogenated**		
14453	61790-39-4	Castor oil fatty acids, hydrogenated**		
14470 42960	8001-78-3	Castor oil, hydrogenated**		
14505	9004-35-7	Cellulose acetate**		
14512	9004-39-1	Cellulose acetate propionate**		
14680	77-92-9	Citric acid		
14685	8001-31-8	Coconut oil**		
14693	8001-30-7	Corn oil**		
14695/1	-	Corn oil fatty acids**		
14698	8001-29-4	Cotton seed oil**		



Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
14700/1	68308-51-0	Cotton seed oil fatty acids**		
15095	334-48-5	n-Decanoic acid		
16697	693-23-2	Dodecanedioic acid		
16775 52730	112-86-7	Erucic acid		
17170	61788-47-4	Coconut fatty acids		
17175	68938-15-8	Coconut fatty acids, hydrogenated**		
17200	68308-53-2	Soya fatty acids		
17215	84625-38-7	Sunflower oil fatty acids**		
17230	61790-12-3	Tall oil fatty acids		
17236	61790-37-2	Tallow oil fatty acids**		
17245	8016-13-5	Fish oil**		
17247/1	-	Fish oil fatty acids**		
17275 55040	64-18-6	Formic acid		
17290	110-17-8	Fumaric acid		
17510 55190	29204-02-2	Gadoleic acid		
18010	110-94-1	Glutaric acid		
18070	108-55-4	Glutaric anhydride		
18124	8016-24-8	Hempseed oil**		
18126/1	-	Hempseed oil fatty acids		
18250 14527	115-28-6	Hexachloroendomethylene-tetrahydrophthalic acid	0.1	
18280	115-27-5	Hexachloroendomethylene-tetrahydrophthalic anhydride		
18770 59360	142-62-1	n-Hexanoic acid		
18880	99-96-7	4-Hydroxybenzoic acid		
18900 61840	106-14-9	12-Hydroxystearic acid		
19150	121-91-5	Isophthalic acid	250	
19270	97-65-4	Itaconic acid		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
19460	50-21-5	Lactic acid		
19470	143-07-7	Lauric acid		
19515	557-59-5	Lignoceric acid**		
19518 64015	60-33-3	Linoleic acid		
19526 64150	28290- 79-1	Linolenic acid		
19532 64160	8001-26- 1	Linseed oil**		
19534/1	68424- 45-3	Linseed oil fatty acids**		
19540 64800	110-16-7	Maleic acid	TOC	
19960 64900	108-31-6	Maleic anhydride	TOC	
19965 65020	6915-15- 7	Malic acid		
19968 65040	141-82-2	Malonic acid		
22350 67891	544-63-8	Myristic acid		
22763 69040	112-80-1	Oleic acid		
22769/1	92044- 96-7	Olive oil fatty acids**		
22775 69920	144-62-7	Oxalic acid	300	
22780 70400	57-10-3	Palmitic acid		
22785 71020	373-49-9	Palmitoleic acid**		
22790/1	-	Palmkernel oil fatty acids**		
22795/1	-	Palm oil fatty acids**		
22867	109-52-4	n-Pentanoic acid (valeric acid)**		
22945	68132- 21-8	Perilla oil**		
22950/1	-	Perilla oil fatty acids**		
23170 72640	7664-38- 2	Phosphoric acid		
23173	1314-56- 3	Phosphoric anhydride**		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
23200 74480	88-99-3	o-Phthalic acid		
23380 76320	85-44-9	Phthalic anhydride		
23730	8002-11-7	Poppy-seed oil**		
23733/1	-	Poppy-seed oil fatty acids**		
23890	79-09-4	Propionic acid		
23950	123-62-6	Propionic anhydride		
24045	8016-49-7	Pumpkin seed oil**		
24047/1	-	Pumpkin seed oil fatty acids**		
24055 13040	89-05-4	Pyromellitic acid**	2.5	
24057	89-32-7	Pyromellitic dianhydride		
24065/1	93165-31-2	Rapeseed oil fatty acids**		
24070 83610	73138-82-6	Resin acids and Rosin acids		
24075 83700	141-22-0	Rizinoleic acid	TOC	
24078	-	Rizinoleic acid, dehydrogenated**		
24100 24130 24190	8050-09-7	Rosin		
24160	8052-10-6	Tall oil rosin		
24260	8001-23-8	Safflower oil**		
24262/1	-	Safflower oil fatty acids**		
24270	69-72-7	Salicylic acid		
24280	111-20-6	Sebacic acid		
24430	2561-88-8	Sebacic anhydride		
24435	8008-74-0	Sesame oil**		
24437/1	-	Sesame oil fatty acids**		
24520	8001-22-7	Soybean oil		
24550	57-11-4	Stearic acid		
24820	110-15-6	Succinic acid		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
24850	108-30-5	Succinic anhydride		
24895	8001-21-6	Sunflower oil**		
24900/1	84625-38-7	Sunflower oil fatty acids**		
24905	8002-26-4	Tall oil**		
24910	100-21-0	Terephthalic acid	325	
24940	100-20-9	Terephthalic acid dichloride		
25540 13050	528-44-9	Trimellitic acid	250	
25550	552-30-7	Trimellitic acid anhydride		
26340	8024-09-7	Walnut oil**		
26345/1	-	Walnut oil fatty acids**	TOC	
36000	50-81-7	Ascorbic acid		
52000	27176-87-0	Dodecylbenzenesulphonic acid	TOC	
80720	8017-16-1	Polyphosphoric acids		
83440	2466-09-3	Pyrophosphoric acid		
92160	87-69-4	Tartaric acid		

### B.3.1.1.9 Other monomers

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
10120	108-05-4	Vinyl acetate	600	
10690	79-10-7	Acrylic acid	300 as acrylic acid	
10780	141-32-2	n-Butyl acrylate		
11470	140-88-5	Ethyl acrylate		
11510 11830	818-61-1	Ethylene glycol monoacrylate		
11710	96-33-3	Methyl acrylate		
11530	999-61-1	2-Hydroxypropyl acrylate	2.5	
13870	106-98-9	Butene		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
10630	79-06-1	Acrylamide	0.1	
10660	15214-89-8	2-Acrylamido-2-methylpropane sulphonic acid	2.5	
11500	103-11-7	2-Ethylhexyl acrylate	2.5	
12100	107-13-1	Acrylonitrile	0.1	
13395	4767-03-7	2,2-Bis(hydroxymethyl) propionic acid	2.5	only as monomers for polymer additives
13630	106-99-0	1,3-Butadiene	0.1	QM = 1mg/kg
14260	502-44-3	Caprolactone	2.5 as the sum of caprolactone and 6-hydroxyhexanoic acid	
14380/ 23155	75-44-5	Carbonyl chloride	0.1	QM = 1 mg/kg
16950	74-85-1	Ethylene		
19490	947-04-6	Lauro lactam	250	
20020	79-41-4	Methacrylic acid	300 as methacrylic acid	
20110	97-88-1	Butyl methacrylate		
21130	80-62-6	Methyl methacrylate		
21190	868-77-9	Ethylene glycol monomethacrylate		
20440	97-90-5	Ethylenglycol dimethacrylate	2.5	
20530	2867-47-2	2-(Dimethylamino)ethyl methacrylate	0.1	
20590	106-91-2	2,3-Epoxypropyl methacrylate	1	QMA = 0.02 mg/6 dm <sup>2</sup>
25120	116-14-3	Tetrafluoro ethylene	2.5	only as monomers for polymer additives
25150	109-99-9	Tetrahydrofuran	30	
26050	75-01-4	Vinyl chloride	0.1	QM = 1mg/kg
26110	75-35-4	Vinyliden chloride	0.1	
22660	111-66-0	1-Octene	TOC	

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
23980	115-07-1	Propylene		
24610	100-42-5	Styrene		

#### B.3.1.1.10 Blocking agents

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
-	96-29-7	2-Butanonoxime*		for hot-cured coatings only
14200 41840	105-60-2	Caprolactam	750	for hot-cured coatings only

#### B.3.1.2 Fillers/Colourants

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
		Colourants		Requirements according to 5.4.2 and 5.4.3 of the general part of the evaluation criteria document
		Fillers and pigments		
34480		Aluminium fibres, -flakes and -powder	20 for Al	
34560	21645-51-2	Aluminium hydroxide		
34690	11097-59-9	Aluminium-Magnesium hydroxy-carbonate		
34720	1344-28-1	Aluminium oxide		
92000	7727-43-7	Barium sulfate	70 for Ba	
41520	1305-78-8	Calcium oxide		
42080	1333-86-4	Soot	PAH as per TrinkwV <sup>7</sup>	Specification as per Regulation (EU) 10/2011
42500		Carbonic acid, salts		
55520		Glass fibres (without glass fibre sizing)		
55600		Glass microballs		
62240	1332-37-2	Iron oxide	20 for Fe	
62720	1332-58-7	Kaolin		

<sup>7</sup> 10 % of threshold values of TrinkwV, Annex 2 / Part II

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
62800	92704-41-1	Kaolin, calcinated		
64720	1309-48-4	Magnesium oxide		
65360	11129-60-5	Manganese oxide	5 for Mn	
67120	12001-26-2	Mica		
83470	14808-60-7	Quartz		
85601		Silicates, natural (except asbestos)		
85610		Silicates, natural, silylated (except asbestos)		
85680	1343-98-2	Silicic acid		
86000	1343-98-2	Silicic acid, silylated		
86240	7631-86-9	Silicon dioxide		Specification as per Regulation (EU) 10/2011
86285	60676-86-0	Silicon dioxide, silylated		
85950	37296-97-2	Silicic acid, magnesium-sodium- fluoride salt		
86160	409-21-2	Silicon carbide		
92080	14807-96-6	Talc		
93440	13463-67-7	Titanium dioxide		Specification as per Regulation (EU) 10/2011
96180	-	Zinc dust*	250 for Zn	
96240	1314-13-2	Zinc oxide		
96200	55799-16-1	Zinc hydroxy phosphite**		

### B.3.1.3 Cementitious fillers

Substance	Restrictions
Cements as per the list of accepted generic constituents <sup>8</sup> in the 4MS common approach 'Assessment of cementitious products in contact with drinking water'	Requirements according to DVGW standard W 347 <sup>9</sup>

<sup>8</sup> [https://www.umweltbundesamt.de/sites/default/files/medien/374/dokumente/cementitious\\_products\\_-\\_4ms\\_common\\_approach\\_jmc\\_final\\_draft\\_sep\\_2018\\_2\\_0.pdf](https://www.umweltbundesamt.de/sites/default/files/medien/374/dokumente/cementitious_products_-_4ms_common_approach_jmc_final_draft_sep_2018_2_0.pdf)

<sup>9</sup> DVGW standard W 347 (May 2006): Hygiene requirements for cement-bound materials intended for use in drinking water supply systems - Testing and evaluation

Aggregates as per the list of accepted generic constituents in the 4MS common approach 'Assessment of cementitious products in contact with drinking water'	Requirements according to DVGW standard W 347
Inorganic additives as per the list of accepted generic constituents in the 4MS common approach 'Assessment of cementitious products in contact with drinking water'	Requirements according to DVGW standard W 347
Organic additives as per the positive list for organic coatings – Table B-1	Requirements as per B.4 and positive list restrictions
Mixing water as per the list of accepted generic constituents in the 4MS common approach 'Assessment of cementitious products in contact with drinking water'	Requirements according to DVGW standard W 347

### B.3.1.4 Modifying agents, organic

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13150	100-51-6	Benzyl alcohol		
47520	-	Dicyclopentadiene-indene-styrene-alpha-methylstyrene-vinyltoluene-isobutylene-copolymer, hydrogenated**	250	
74560	85-68-7	Benzyl butyl phthalate	1500	
74640	117-81-7	Bis(2-ethylhexyl)phthalate	75	
74880	84-74-2	Dibutyl phthalate	15	
75105	68515-49-1 26761-40-0	Phthalic acid, diester with primary saturated (C <sub>9</sub> -C <sub>11</sub> ) alcohols, > 90 % C <sub>10</sub>	450	
92200	6422-86-2	Bis(2-ethylhexyl)terephthalate	TOC	

### B.3.1.5 Solvents

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
13840	71-36-3	1-Butanol		
25150	109-99-9	Tetrahydrofuran	30	
30045	123-86-4	Butyl acetate		
30140	141-78-6	Ethyl acetate		
30295	67-64-1	Acetone		
40594	75-65-0	tert-Butanol**	500	
48030	112-34-5	Diethylene glycol monobutyl ether**	150	



48050	111-90-0	Diethylene glycol monoethyl ether**		
53765	111-76-2	Ethylene glycol monobutyl ether (Butyl glycol)**		
53820	110-80-5	Ethylene glycol monoethyl ether**		
16999	112-25-4	Ethylene glycol monohexyl ether**		
53860	109-86-4	Ethylene glycol monomethyl ether**		
49540	67-68-5	Dimethyl sulphoxide		
52800	64-17-5	Ethanol		
53255	100-41-4	Ethylbenzene**	30	
66620	75-09-2	Dichloromethane**		
66655	78-93-3	Methyl ethyl ketone**	250	
66725	108-10-1	Methyl isobutyl ketone**	250	
81882	67-63-0	2-Propanol, Isopropanol		
93540	108-88-3	Toluene**	60	
95855	7732-18-5	Water	as per TrinkwV	
26945 95945	1330-20-7	Xylene**	60	

### B.3.1.6 Propellant

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
-	115-10-6	Dimethyl ether*	< 1	

### B.3.1.7 Additives and polymerisation production aids

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
	-	Polymeric additives made of monomers under B.3.1.1.9		
12786	919-30-2	3-Aminopropyltriethoxysilane	2.5	
	119345-04-9	Benzene, 1,1'-oxybis-, tetrapropylene derivatised, sulphonated, sodium salts	450	
21498	2530-85-0	[3-(Methacryloxy)propyl]trimethoxysilane	2.5	
26305	78-08-0	Vinyltriethoxysilane	2.5	
26320	2768-02-7	Vinyltrimethoxysilane	2.5	
43120	8001-78-3	Castor oil, hydrogenated		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
57520	31566-31-1	Glycerol monostearate**		
19960	108-31-6	Maleic anhydride	TOC	
66930	68554-70-1	Methylsilsesquioxane		< 1mg Methyltrimethoxysilane /kg Methylsilsesquioxane
69760	143-28-2	Oleyl alcohol		
76960	25322-68-3	Polyethylene glycol		
81840	57-55-6	1,2-Propandiol		
30280	108-24-7	Acetic anhydride		
34230	-	Alkyl(C <sub>8</sub> -C <sub>22</sub> )sulphonic acid	300	
33801	-	n-Alkyl(C <sub>10</sub> -C <sub>13</sub> )benzenesulphonic acid	1500	
34240	91082-17-6	n-Alkyl(C <sub>10</sub> -C <sub>21</sub> )sulphonic acid phenylester	2.5	
35600	1336-21-6	Ammonium hydroxide	50 as NH <sub>4</sub> <sup>+</sup>	
37280	1302-78-9	Bentonite		
37520	2634-33-5	1,2-Benzothiazolin-3-one**	25	for in-can preservation only
38560	7128-64-5	2,5-Bis(5-tert-butyl-2-benzoxazolyl)thiophene	30	
39090	-	N,N-Bis(2-hydroxyethyl)alkyl-(C <sub>8</sub> -C <sub>18</sub> )amine	60 as tertiary amine	
42500	-	Carbonic acid, salts		
42720	8015-86-9	Carnauba wax		
43730	55965-84-9	Mixture of 5-Chloro-2-methyl-2H-isothiazol-3-one and 2-Methyl-2H-isothiazol-3-one 3:1**	7.5	for in-can preservation only, QMA = 25 µg/dm <sup>2</sup>
43760	26172-55-4	5-Chloro-2-methyl-2H-isothiazol-3-one**	0.5	for in-can preservation only
45640	5232-99-5	2-Cyano-3,3-diphenyl ethyl acrylate	2.5	
45705	166412-78-8	1,2-Cyclohexyl dicarbonic acid diisononyl ester	TOC	
46640	128-37-0	2,6-Di-tert-butyl-p-cresole	150	
50640	3648-18-8	Di-n-octyltin dilaurate	0.3 as Sn	
53520	110-30-5	N,N'-Ethylene-bis-stearamide		
58960	57-09-0	Hexadecyltrimethylammonium bromide	300	
59120	23128-74-7	1,6-Hexamethylenebis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionamide]	TOC	

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
60480	3896-11-5	2-(2'-Hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole	TOC	
60560	9004-62-0	Hydroxyethyl cellulose		
61600	1843-05-6	2-Hydroxy-4-n-octyloxybenzophenone	300	
62140	6303-21-5	Hypophosphorous acid		
63760	8002-43-5	Lecithin		
64270	7447-41-8	Lithium chloride**	30 for Li	
66715	693-98-1	2-Methylimidazole*	2.5	
66755	2682-20-4	2-Methyl-4-isothiazolin-3-one	25	for in-can preservation only
67850	8002-53-7	Montan wax		
68320	2082-79-3	Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate	300	
71680	6683-19-8	Pentaerythritoltetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]		
74240	31570-04-4	Tris(2,4-di-tert-butylphenyl)-phosphite		
76721	63148-62-9	Polydimethylsiloxane MW > 6800 Da		Specification as per Regulation (EU) No 10/2011
77360	9005-07-6	Polyethylene glycol dioleate**	TOC	
77520	61791-12-6	Polyethylene glycol ester with castor oil	TOC	
77600	61788-85-0	Polyethylene glycol ester with hydrogenated castor oil		
77702	-	Polyethylene glycol esters of aliphatic monocarbonic acids (C <sub>6</sub> -C <sub>22</sub> ) and their ammonium and sodium sulphates		
77895	68439-49-6	Polyethylene glycol (EO=2-6) monoalkyl(C <sub>16</sub> -C <sub>18</sub> )ether	2.5	
	69011-36-5	Isotridecanol, ethoxylated	90	Specification for polymer: maximum residue of 0.2 mg ethylene oxide/kg
78160	9004-96-0	Oleic acid, ethoxylated**	TOC	
79550	9014-85-1	2,4,7,9-tetramethyl-5-decyn-4,7-diol ether, ethoxylated **		For sintered PTFE coating only

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
80000	9002-88-4	Polyethylene wax		
80077	68441-17-8	Polyethylene wax, oxidised	TOC	
80160	37349-34-1	Polyglycerol-5-stearate**		
80480	82451-48-7	Poly(6-morpholino-1, 3, 5-triazin-2,4-diyl)-[(2, 2, 6, 6-tetramethyl-4-piperidyl)imino]-hexamethylene-[(2, 2, 6, 6-tetramethyl-4-piperidyl)-imino]	250	
80640	-	Silicone polyether, polyoxyalkyl(C <sub>2</sub> -C <sub>4</sub> )dimethyl-polysiloxane		
81870	35674-65-8	N,N'-Propane-1,3-diylbis[N'-octadecyl urea]	2.5	
85360	109-43-3	Dibutyl sebacate	TOC	
86000	67762-90-7	Silicon dioxide, reaction product with polydimethylsiloxane		
86240/8 5580	7631-86-9	Silicon dioxide		Specification as per Regulation (EU) No 10/2011
87680	1338-43-8	Sorbitan monooleate		
80720	8017-16-1	Polyphosphoric acids		
87760	26266-57-9	Sorbitan monopalmitate		
91530	-	Sulphosuccinic acid, alkyl (C <sub>4</sub> -C <sub>20</sub> ) or cyclohexyl diester, salts	250	
95020	6846-50-0	2,2,4-Trimethyl-1,3-pentanediol-diisobutyrate	250	
95859	-	Waxes, refined, derived from petroleum-based or synthetic hydrocarbon feedstocks, high viscosity		Specification as per Regulation (EU) No 10/2011
95883	-	White mineral oil, paraffinic, derived from petroleum-based hydrocarbon feedstocks		Specification as per Regulation (EU) No 10/2011
95935	11138-66-2	Xanthan gum		

### B.3.1.8 Photoinitiators for adhesives

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
38240	119-61-9	Benzophenone	30	
48640	131-56-6	2,4-Dihydroxybenzophenone	300	
48720	611-99-4	4,4'-Dihydroxybenzophenone		
92470	106990-43-6	N,N',N'',N'''-Tetrakis(4,6-bis(butyl(N-methyl-2,2,6,6-tetramethyl-piperidin-4-yl)amino)triazin-2-yl)-4,7-diazadecan-1,10-diamine	2.5	
94000	102-71-6	Triethanolamine	2.5	
94560	122-20-3	Triisopropanolamine	250	

Additionally, all substances listed under Solvents, Organic modifying agents, Binding agents or Fillers/Colourants.

### B.3.1.9 Aids to Polymerisation

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
-	7727-54-0	Ammonium persulphate*	50 as NH <sub>4</sub> <sup>+</sup>	
-	7727-21-1	Potassium persulphate*		
	7775-27-1	Sodium persulphate		
94000	102-71-6	Triethanolamine	2.5	
67680	27107-89-7	Mono-n-octyltin-tris(2-ethylhexylthioglycolate)	60 as Sn	
50320	15571-58-1	Di-n-octyltin-bis(2-ethylhexylthioglycolate)	0.3 as Sn	
51040	15535-79-2	Di-n-octyltin thioglycolate		
93420	7646-78-8	Tin(IV)chloride**		

Explanation:

\* Substances which have been assessed nationally in the context of this evaluation criteria document.

\*\* Substances that are assessed by another EU Member State as part of the 4MS initiative and adopted by the other states (listed in the 4MS Core List).

## B.3.2 Intermediate products

The list of intermediate products is informative. It illustrates the reaction paths taken into account when determining the positive list. Due to the diversity of possible reaction paths, the list of possible intermediate products is not exhaustive. The starting substances for manufacturing intermediate products must appear in Table B-1.

Some examples are given below:

Tabelle B-2 Intermediate products

German designation	English designation	Components
<b>Intermediate products with epoxy groups</b>		
BPA-Harze	Bisphenol A resins	Epichlorhydrin, Bisphenol A
BPF-Harze	Bisphenol F resins	Epichlorhydrin, Bisphenol F
Phenol-Novolac-Harze (nur für Pulverlacke)	Phenol novolac resins	Bisphenol F diglycidyl ether
Epoxyesterharze	Epoxyester resins	Epoxy resins, fatty acids
<b>Intermediate products with amines</b>		
Kondensationsprodukt von Aldehyd und Polyamin	Condensation product of aldehyde and polyamine	Aldehydes, Amines
Mannich Basen und Salze hiervon	Mannich base and salts thereof	Phenols, formaldehyde, amines
Michael-Additionsprodukte	Michael addition products	unsaturated compounds like e.g. unsaturated acids, amines
Polyaminoamide	Polyaminoamides	Monomeric fatty acids, dimeric fatty acids, amines
<b>Intermediate products with isocyanates</b>		
Urethanpolyamine	Urethane polyamines	Isocyanates, amines
Poly-/Oligomere von Isocyanaten (Uretdion, Isocyanurat, Biuret)	Polymers or Oligomers of Isocyanates	Isocyanates
Blockierte Isocyanate (nur für heißhärtende Beschichtungen)	blocked Isocyanates	Isocyanates, caprolactam, butanonoxime
Prepolymere Vorpolymere	Prepolymers	Isocyanates, alcohols, amines
<b>Various polymer types</b>		
Polyacrylate	Polyacrylates	
Copolymer aus Ethylacrylat und Ethylhexylacrylat	Ethylacrylate-Ethylhexylacrylate -copolymer	Ethyl acrylate, ethylhexyl acrylate
Polybutylacrylate	Polybutylacrylates	Butyl acrylat
Polymethacrylate	Polymethacrylates	
Poly(meth)acrylatpolyole	Poly(meth)acrylate polyols	Acrylic acid, methacrylic acid, alcohols
Polyethylenglycoldiacrylat	Polyethyleneglycoldiacrylate	Polyethylene glycol, acrylic acid

German designation	English designation	Components
Polyacrylnitrilpolyole	Polyacrylonitrile Polyols	Acrylic acid, methacrylic acid, acrylonitrile, alcohols
Polyetherpolyole	Polyether Polyols	Oxirane compounds, alcohols, tetrahydrofuran, amines
Polyesterpolyole	Polyester Polyols	Carboxylic acids, alcohols
Polyamid	Polyamide	Lactams
Phenol-Formaldehydharze	Phenol formaldehyde resins	Phenols, formaldehyde
Harnstoff-Formaldehydharze	Urea formaldehyde resins	Formaldehyde, urea
Copolymer aus Vinylidenchlorid	Vinylidene chloride copolymer	Vinylidene chloride, other monomers

## B.4 Additional requirements

The additional requirements laid down in Table B-3 apply to the various binding agent systems of organic coatings. The general part of the evaluation criteria document for organic materials must be observed.

In case of combinations of different types of binding agents, the additional requirements shall be met for all types of binding agents included.

Table B-3 List of additional requirements for the different binding agent systems

Substances/substance groups	Restriction MTC <sub>tap</sub> in µg/l	Test method (Other equivalent test methods may be used)
<i>a) Coatings containing epoxy resins</i>		
Bisphenol A	2.5 <sup>10</sup>	DIN EN 13130-13: 2005-05
Bisphenol F	2.5	DIN EN 13130-13: 2005-05
BADGE including their hydrolysis products	450	Official method <sup>11</sup> L 00.00-51
BFDGE including their hydrolysis products	2.5	Official method L 00.00-51
NOGE isomers with M < 1000 Da including hydrolysis products	2.5	DIN EN 15137: 2006-06

<sup>10</sup> <https://www.umweltbundesamt.de/en/document/new-regulation-on-bisphenol-a-consequences-for>

<sup>11</sup> Official methods for analysing food: Official collection of analysis procedures under § 64 LFGB [German Food and Feed Code] (formerly § 35 LMBG): <https://www.methodensammlung-bvl.de/de/dokumente> (in German)

Substances/substance groups	Restriction MTC <sub>tap</sub> in µg/l	Test method (Other equivalent test methods may be used)
Epichlorhydrin and 3-Monochloro-1,2-propandiol (hydrolysis product)	0.1 6	DIN EN 14207: 2003-09 official method <sup>12</sup> B80.56-2
Formaldehyde	750	Notification 50 (Federal Health Gazette 30 (1987)368)
Primary aromatic amines	0.1	specific detection by GC-ECD/GC-MS with derivatisation <sup>13</sup>
<i>b) Coatings containing polyurethanes</i>		
Total of all isocyanates	QM = 1mg/kg	DIN EN 13130-8: 2004-08
Alternatively, hydrolysing amines may be determined in migration waters		
Primary aromatic amines	0.1	specific detection by GC-ECD/GC-MS with derivatisation
<i>c) Coatings containing polyesters</i>		
<i>d) Coatings containing polyacrylates</i>		
Acrylates	300 as acrylic acid	
<i>e) Polyamides</i>		
Primary aromatic amines	0.1	specific detection by GC-ECD/GC-MS with derivatisation
<i>f) Reaction products of photoinitiators for adhesives</i>		

## B.5 Regulation on the hygienic evaluation of anaerobic adhesives in contact with drinking water

Generally, anaerobic adhesives cross-link to polyacrylates and polymethacrylates with the help of catalysts. The following starting substances are typically used:

Mono-/multifunctional acrylates and/or mono-/multifunctional methacrylates (e.g. (meth-)acrylate terminated compounds in the form acrylate-R-acrylate and/or acrylate-r, where r = organic residue such as H, urethane, epoxy, acrylate, aliphatic and aromatic residue, polyol) with content of > 60 % in relation to the end-product, which cross-link to polyacrylates/polymethacrylates with the help of catalysts (e.g. peroxide and amine).

<sup>12</sup> Official methods for analysing food: Official collection of analysis procedures under § 64 LFGB [German Food and Feed Code] (formerly § 35 LMBG): <https://www.methodensammlung-bvl.de/de/dokumente> (in German)

<sup>13</sup> Test method: Pietsch et al (1996) Fresenius J. Anal. Chem. 355:164-173 or Pietsch et al. (1997) Vom Wasser 88: 119-135



Other starting substances include plasticizers, fillers, thickeners, aids to polymerisation, additives such as stabilisers and colourants.

The positive list of Annex B, Table B-1 of this evaluation criteria document, which also includes air-curing adhesives such as epoxy resin adhesives, does not cover the typical formulations for anaerobic adhesives. In addition, there is no possibility of testing these products according to the migration testing as per DIN EN 12873-1 or -2.

The contact areas of the cured anaerobic adhesive with drinking water are smaller than for seals in drinking water distribution. Therefore, potential migration of starting substances from the cured adhesive can be estimated as (very) low.

As regards the factory application of anaerobic adhesives, it can be assumed that the curing takes place exhaustively under the (optimal) conditions specified and no measurable amount of migration into the water distribution system occurs. When used on-site, too much adhesive could be wrongly applied to the thread. If these amounts are not left to react, the drinking water may become contaminated. For this reason, proper application is important. The industry federation *Klebstoffe e.V.* has issued guidance<sup>14</sup> (in German) on proper application.

If applied properly, anaerobic adhesives as described above should not have any adverse impact on drinking water quality.

Anaerobic adhesives do not require a certificate of conformity.

---

<sup>14</sup> <https://www.klebstoffe.com/die-welt-des-klebens/informationen/publikationen/merkblaetter/verschiedenes.html> (in German)

# **Annex C            Lubricants**

## **C.1    Scope of application**

This annex applies to lubricants.

Lubricants reduce friction and wear in a tribological system in which the surfaces of two components are in moving contact with one another. Lubricants within the meaning of this guideline can come into direct contact with drinking water. Lubricants are broken down into liquid, plastic rigid and solid types. These lubricants must be classed as a building element/component in a drinking water or sanitary installation.

Food technology lubricants, which demonstrate compliance with DIN EN ISO 21469 or other international regulations, are not exempt from a hygienic assessment before use in drinking water in accordance with this evaluation criteria document.

Sliding or fitting lubricants, metal machining lubricants and other lubricants are not covered by the scope of application.

## **C.2    Information on lubricants**

Lubricants for use with fittings are generally composed of the base oil, the thickener and if necessary a low dose of additives or adjuvants. Base oils are the principal component and account for more than 50 % of the lubricant. Thickeners account for approximately 20 % of the lubricant. Additives and polymerisation production aids are used to create specific properties such as corrosion protection and are added to lubricants in amounts of approximately 2 %.

The content information mentioned is used solely to classify technological function, they are not relevant for compliance with the positive list.

## **C.3    Composition requirements**

### **C.3.1    Positive list for lubricants**

Only the starting substances listed in Table C-1 may be used to manufacture lubricants in contact with drinking water.

For unlisted starting substances, the requirements for unlisted starting substances apply, including their contaminants and degradation and reaction products (see Chapter 5.2.2 of the general part of the evaluation criteria document for organic materials). The requirements according to Chapter 5.4.3 of the general part of the evaluation criteria document for organic materials apply to colourants.

Table C-1 Positive list for lubricants

**C.3.1.1 Base oils**

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
-	-	Cyclic Organopolysiloxanes with methyl groups only or n-alkyl groups (C <sub>2</sub> -C <sub>32</sub> ) *		composition in accordance with BfR Recommendation XV <sup>15</sup>
-	70131-67-8	Polydimethylsiloxane, hydroxy terminated*		composition in accordance with BfR Recommendation XV <sup>15</sup>
14411 42880	8001-79-4	Castor oil		
14440 42960	64147-40-6	Castor oil, dehydrogenated		
-	68083-14-7, 73138-88-2, 68440-81-3	Silicone oils with methyl and phenyl groups, linear and branched*		composition in accordance with BfR Recommendation XV <sup>15</sup>
17200	68308-53-2	Soya fatty acids		
17236	61790-37-2	Tallow oil fatty acids		
	163149-29-9	Polyalphaolefin from 1-Dodecene and 1-Octene		average molecular weight at least 440 Da, viscosity at 100°C at least 3.8 cSt ( $3,8 \times 10^{-6} \text{ m}^2/\text{s}$ ); polymerisation production aids and additives less than 0.02 % (w/w) in polymer
66930	68554-70-1	Methylsilsesquioxane		< 1mg Methyltrimethoxysilane /kg Methylsilsesquioxane
76520	9003-29-6	Polybutene*		Composition as per Annex A
76530	68937-10-0	Polybutene, hydrogenated*		Composition as per Annex A

<sup>15</sup> [https://bfr.ble.de/kse/faces/DBEmpfehlung\\_en.jsp](https://bfr.ble.de/kse/faces/DBEmpfehlung_en.jsp)

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
76685	68037-01-4	Poly 1-Decene, hydrogenated		residual hydrocarbon contamination with carbon number less than 30: not exceeding 1.5 %, free of naphthenes, aromatic compounds, PAKs
76721	63148-62-9	Polydimethylsiloxane MW > 6800 Da		Specification as per Regulation (EU) No 10/2011
76721	9016-00-6, 63148-62-9, 68037-74-1	Methyl silicone oil: linear and branched*		Composition in accordance with BfR Recommendation XV <sup>15</sup>
76950 80000	9002-88-4	Polyethylene*		Composition as per Annex A
80360	9003-27-4	Polyisobutylene*		Composition as per Annex A
95858	-	Waxes, paraffinic, refined, derived from petroleum-based or synthetic hydrocarbon feedstocks, low viscosity	2.5	Specification as per Regulation (EU) No 10/2011
95883	-	White mineral oils, paraffinic, derived from petroleum-based hydrocarbon feedstocks		Specification as per Regulation (EU) No 10/2011
-	68604-46-6	Lithium salt of castor oil fatty acids, hydrogenated*	30 for Li	

### C.3.1.2 Thickener

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
10090 30000	64-19-7	Acetic acid		
10599/ 56	-	Calcium salts of linear, aliphatic, saturated monovalent carboxylic acids C <sub>10</sub> -C <sub>20</sub> *		
13090 37600	65-85-0	Benzoic acid		
18900 61840	106-14-9	12-Hydroxystearic acid		
24550	57-11-4	Stearic acid		

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
89040				
34720	1344-28-1	Aluminium oxide		
41280	1305-62-0	Calcium hydroxide		
54450	-	Fats and oils, from animal or vegetable food sources		
54480	-	Fats and oils, hydrogenated, from animal or vegetable food sources		
66240	9004-67-5	Methyl cellulose (gelling agent)		
69885	68988-56-7	Silicon dioxide, reaction product with trimethylchlorosilane and isopropylalcohol*		Composition in accordance with BfR Recommendation XV <sup>15</sup>
81160	9002-84-0	Polytetrafluorethylene*	2.5 for tetrafluoroethylene	
83560	68953-58-2	Dialkyldimethylammonium-aluminium silicate*		
85680	1343-98-2	Silicic acid		Purity requirements for fillers according to Chapter 5.4.2 (general part)
86240	7631-86-9	Silicon dioxide		Specification as per Regulation (EU) No 10/2011
86285	68611-44-9	Silicon dioxide, reaction product with dimethyldichlorosilane*		
86285	68909-20-6	Silicon dioxide, reaction product with hexamethyldisilazane*		
86285	67762-90-7	Silicon dioxide, reaction product with polydimethylsiloxane*		
-	54326-11-3	Aluminium stearoyl benzoyl-hydroxide*		
-	71011-24-0	Quarternary ammonium compounds, benzyl(hydrogenated tallow-alkyl)dimethyl, salts with bentonite*		
-	-	reaction product of sebacic acid with stearylamine, neutralised with calcium hydroxide*		
-	7620-77-1	Lithium salt of 12-Hydroxystearic acid*	30 for Li	

### C.3.1.3 Additives

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
-	637-12-7	Aluminium tristearate*		
40320	10043-35-3	Boric acid	100 for B	
40400	10043-11-5	Boron nitride		
40720	25013-16-5	tert-Butyl-4-hydroxyanisole (BHA)	TOC	
45940 15095	334-48-5	n-Decanoic acid		
46640	128-37-0	2,6-Di-tert-butyl-4-cresol (BHT)	150	
52800 16780	64-17-5	Ethanol		
53600	60-00-4	Ethylenediaminetetraacetic acid (EDTA)	60	
59200	35074-77-2	1,6-Hexamethylene-bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate]	300	
66655 21827	78-93-3	Methyl ethyl ketone*	250	
68320	2082-79-3	Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate	300	
71680	6683-19-8	Pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate]		
74240	31570-04-4	Tris(2,4-di-tert-butylphenyl)-phosphite		
85030 24280	111-20-6	Sebacic acid		
86160	409-21-2	Silicon carbide		Purity requirements for fillers according to Chapter 5.4.2 (general part)
92880 92900	41484-35-9	Thiodiethylene-bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]	120	
95858	-	Waxes, paraffinic, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, low viscosity	2.5	Specification as per Regulation (EU) No 10/2011
95859	-	Waxes, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, high viscosity		Specification as per Regulation (EU) No 10/2011

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
96240	1314-13-2	Zinc oxide	250 for Zn	Purity requirements for fillers according to Chapter 5.4.2 (general part)

### C.3.1.4 Polymerisation production aids

Ref. No	CAS No	Substance	Restriction MTC <sub>tap</sub> in µg/l	Other restrictions
-	108-32-7	Propylene carbonate*		
16960 15272	107-15-3	Ethylenediamine	600	
42500	-	Carbonic acid, salts		Purity requirements for fillers according to Chapter 5.4.2 (general part)
52720	112-84-5	Erucic acid amide		
53520	110-30-5	N,N'-Ethylene-bis-stearamide		
72640 23170	7664-38-2	Phosphoric acid		Purity requirements for fillers according to Chapter 5.4.2 (general part)
81840 23740	57-55-6	1,2-Propanediol		
83440	2466-09-3	Pyrophosphoric acid		Purity requirements for fillers according to Chapter 5.4.2 (general part)
83470	14808-60-7	Quartz		
92080	14807-96-6	Magnesium silicate (talcum)		
93440	13463-67-7	Titanium dioxide		
96320	1314-98-3	Zinc sulfide	250 for Zn	

\* Substances that are assessed nationally

## C.4 Specification of testing for lubricants

### C.4.1 Test samples

Lubricant testing involves the lubricant to be tested being applied to a glass plate measuring 200 mm × 200 mm at a thickness of 1 mm.

### C.4.2 Surface/volume ratio

For testing as per DIN EN 12731-1: 2014-09 a surface to volume ratio of 5 dm<sup>-1</sup> is used.

For testing as per DIN EN 1420-1: 2016-05 a surface to volume ratio of 0.2 dm<sup>-1</sup> is used.

### **C.4.3 Conversion factor**

The conversion requirements laid down in Table 7 of the general part of this evaluation criteria document shall apply. For lubricants used in kitchen or sanitary fittings, the conversion factor ( $F_c$ ) of 0.2 d/dm is used to calculate ctap.

## **Annex D Elastomers (informative)**

Elastomers do not currently fall under the scope of this evaluation criteria document. To demonstrate suitability for use in contact with drinking water, the elastomer guideline<sup>16</sup> can be used with the KTW transitional regulation<sup>17</sup> and the updated positive list (<https://www.umweltbundesamt.de/dokument/aktualisierte-positivliste-anlage-1-teil-1-zur>; German version only).

## **Annex E Thermoplastic elastomers (TPE) (informative)**

Thermoplastic elastomers do not currently fall under the scope of this evaluation criteria document. To demonstrate suitability for use in contact with drinking water, the transitional recommendation<sup>18</sup> can be used.

## **Annex F Silicones (informative)**

Silicones do not currently fall under the scope of this basis for assessment. To demonstrate suitability, the transitional regulation on the hygienic assessment of silicones in contact with drinking water can be used (document currently in preparation).

---

<sup>16</sup> <https://www.umweltbundesamt.de/en/document/guideline-for-hygienic-assessment-of-elastomers-in>

<sup>17</sup> <https://www.umweltbundesamt.de/en/document/elastomer-guideline-extended-transitional-rule-for>

<sup>18</sup> <https://www.umweltbundesamt.de/en/document/recommendation-on-the-provisional-hygienic>